

# KAMA 2600 ENVELOPE WINDOW FILM

## CAPABILITIES

- Gauge: .001" to .002" (0.00115 Standard)
- Width: 2" to 80" (51 to 2032)
- Core Size: 3" and 6" standard cores, 8" available
- Roll O.D.: 29" standard, available up to 40"
- 3 strategic manufacturing locations

## PROPERTIES

- Low gloss formula for better optical character recognition
- Low dust for higher production rates
- Engineered orientation for optimal tear properties
- Specially formulated to reduce scratching
- Excellent stiffness for improved processability

## TECHNICAL SPECIFICATIONS

	Value	Units	ASTM
Specific Gravity	1.05	grams/cm <sup>2</sup>	
Yield	26,360	in <sup>2</sup> /lb./mil of thickness	
Tensile Strength at Yield	8,000 to 12,000	psi	D638
Ultimate Elongation	3 to 10	%	D638
Tensile Modulus	400,000 to 450,000	psi	D790

## CHEMICAL RESISTANCE

- Acid Resistance.....Good to Excellent
- Strong Oxidizers.....Poor
- Alkalies .....Excellent
- Hydrocarbon Solvents.....Poor
- Alcohols.....Good to Excellent
- Fat, Grease, and Oil.....Good

## CAPABILITIES AND TECHNICAL SPECIFICATION

The capabilities we list reflect the standard capabilities we offer at the time of this printing. Our capabilities are likely to broaden as we add capacity and expand our product offering. Please call our Sales Team to further discuss your specific needs.

The data herein represents typical values by the methods indicated and should be so considered. Processing variables are a major factor in product performance, this information should serve only as a guide. To the best of our knowledge the data is correct. No warrant is made or implied. The corporation assumes no obligation or liability for the use of data presented.



YOUR TOTAL RESOURCE FOR  
EXTRUDED SHEET & FILM

800.628.7598